



## VRLA Rechargeable Battery

# HR5.5-12



### FEATURES

- Maintenance free(no water topping-up required)
- No free acid(Non-spillable battery)
- Can be used in any orientation(excluding used inverted)
- The battery is designed for high rate usage
- Its design life is up to 6 years in floating application
- Absorbent Glass Mat technology for efficient gas recombination
- The power density at 5 min~15min discharging rate is 30% higher than BP series

### APPLICATION

- UPS
- Emergency Lights
- Toy-Cars
- Fishing Lights
- Power Packs

### SPECIFICATIONS

Nominal Voltage	12V	
Nominal Capacity	10 Hour Rate (500mA, 10.5V)	5.00 Ah
	15 Min Rate (132W, 7.8V)	2.75 Ah
Approx. Weight	1800g(3.97lbs.)	
Terminals	T1 (Faston Tab 187) T2 is optional	
Max. Discharge Current	75 A (5 sec.)	
Max. Charge Current	1.50 A	
Operating Temperature Range	Charge	0°C~40°C(32°F~104°F)
	Discharge	-20°C~50°C(-4°F~122°F)
	Storage	-20°C~40°C(-4°F~104°F)
Self Discharge	< 3% per month (25°C)	
Internal Resistance	≤ 27mΩ (Fully Charged)	



### CONTAINER MATERIAL


- Standard: ABS( UL 94-HB)  
Model Name: HR5.5-12
- Optional: Flame Retardant ABS (UL 94-V0)  
Model Name: HR5.5-12FR




- IEC 61056-1
- JIS C 8702-1
- GB/T 19639.1

### OUTER DIMENSIONS mm(inch)


Length (L)	Width (W)	Container Height (H)	Total Height (TH)
90±1.5(3.54±0.06)	70±1.5(2.76±0.06)	102±1.5(4.02±0.06)	106±2.0(4.17±0.08)




### TERMINAL TYPE



**HR5.5-12 (HR5.5-12FR) discharge characteristics (25°C/77°F)**




**Battery Charging Characteristics**



**Charging Procedure**

Application	Charging method	Charging Voltage at 25°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C/cell)	Max. charging current (CA)	Charging time 0.1CA, 25°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power Source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service		2.40~2.50	-4	0.3	16	10	

**Effect Of Temperature On Long Term Float Life**



**Constant power discharge characteristics at 25 °C/77 °F Unit: W**

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	20 Min	30 Min	40 Min	50 Min	60 Min	120 Min
1.80V	225.5	154.0	111.5	95.2	72.4	55.0	46.0	40.5	22.3
1.70V	269.5	171.9	121.3	100.8	75.4	57.1	47.4	41.4	22.7
1.60V	288.8	180.8	126.8	104.5	77.0	58.4	48.4	42.1	23.1
1.50V	297.0	184.3	129.6	106.2	78.0	59.2	49.0	42.5	23.2
1.40V	302.5	186.8	131.0	107.1	78.5	59.5	49.4	42.8	23.3
1.30V	305.3	188.4	132.0	107.8	79.0	59.8	49.6	42.9	23.3

**Constant current discharge characteristics at 25 °C/77 °F Unit: A**

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	20 Min	30 Min	40 Min	50 Min	60 Min	120 Min
1.80V	20.13	13.51	9.65	8.16	6.14	4.63	3.85	3.38	1.86
1.70V	24.50	15.08	10.49	8.64	6.39	4.80	3.97	3.45	1.89
1.60V	26.25	15.86	10.97	8.96	6.53	4.91	4.05	3.51	1.93
1.50V	27.00	16.17	11.21	9.11	6.61	4.98	4.10	3.54	1.93
1.40V	27.50	16.39	11.33	9.19	6.65	5.00	4.13	3.57	1.94
1.30V	27.75	16.53	11.42	9.25	6.69	5.03	4.15	3.58	1.94

All data and artworks shall be changed without prior notice, BBT reserves the right to explain and update the information contained herein.  
For operation, please refer to the instruction from technical manual.

A/0 REV. July, 2016

**USA:**  
B&B BATTERY(USA) INC.  
6415 RANDOLPH ST.COMMERCE,CA,90040 U.S.A.  
TEL:1-323-278-1900.1-800-278-8599  
FAX:1-323-278-1268  
E-Mail:sales@bb-battery.com

**CHINA FACTORY:**  
B.B. TECH(CHANGSHA) CO., LTD.  
No.57 DongsiRoad, Changsha National Economic & Technical Development Zone, Changsha, Hunan PRC  
TEL:86-731-82955888  
FAX:86-731-82955111  
E-Mail:maggy@bb-battery.com

**EUROPE:**  
B&B BATTERY(EUROPE) B.V.  
SUITE 8, HAAKSBERGWEG 33, 1101 BP AMSTERDAM, THE NETHERLANDS  
TEL: 31-30-320-0190  
MOBILE: 852-9128-2711  
E-Mail: dliu@bb-battery.com

**HONG KONG:**  
B&B BATTERY(Hong Kong) Co.  
TEL:852-2311-4918  
FAX:852-2739-1182  
E-Mail:bbhk@hkstar.com

**JAPAN:**  
B&B BATTERY(JAPAN) CO., LTD.  
1375-11 NARAHARA-MACHI,HACHIOJI, TOKYO 193-0803,JAPAN.  
TEL:81-426-25-6375  
FAX:81-426-25-6375  
E-Mail:miyata@bb-battery.com

**TAIWAN:**  
B.B. BATTERY(TAIWAN) CO., LTD.  
TEL:886-6-502-5150  
FAX:886-6-589-8087  
E-Mail:kevinlin@bb-battery.com